

IN THE CLAIMS:


Please cancel Claims 6, 7 and 8.

1. (Currently Amended) A dispersion comprising polyanions and cationic 3,4-polyalkylenedioxythiophenes and water or a water/alcohol mixture as a solvent, wherein about 90% of the particles of the dispersion are less than 50 nm and wherein the resistivity of the coatings produced therefrom by building a dispersion film and removing the solvent from the dispersion film is at least ~~is more than~~ 5000 Ω cm, wherein the weight ratio of cationic 3,4-polyalkylene-dioxythiophene to polyanion have a ratio ranging from between about 1:8 and about 1:25 and which was treated by high pressure homogenization applying a pressure from 100 to 1000 bar.

2. (Currently Amended) The dispersion according to Claim 1, wherein at least ~~about~~ 90% of the particles are less than about 40 nm.

3. (Cancelled)

4. (Previously Presented) The dispersion according to Claim 1, wherein the 3,4-polyalkylenedioxythiophenes are compounds of the formula (I)



wherein

n is an integer from 3 to 100, preferably from 4 to 15, and

X is $-(CH_2)_x-CR^1R^2-(CH_2)_y-$, where

R^1 and R^2 , independently of one another, are H, an alkyl radical having from 1 to 20 carbon atoms, an aryl radical having from 6 to 14 carbon atoms or $-CH_2-OR^3$, where R^3 is H, alkyl or $-CH_2-CH_2-CH_2-SO_3H$, and

x and y are each, independently of one another, an integer from 0 to 9.

Mo6935

- 2 -

5. (Original) The dispersion according to Claim 1, wherein the dispersion is a 3,4-polyethylenedioxythiophene/polystyrene sulfonate dispersion.

6. (Cancelled)

7. (Cancelled)

8. (Cancelled)

9. (Previously Presented) A dispersion according to Claim 4, wherein n is an integer from 4 to 15.

Mo6935

- 3 -